

MEI-62(CuZn37 Sn1.5) ROLLED PRODUCTS

CHEMICAL COMPOSITION(%)		
Cu	61.00-63.50	
Tin	1.0-1.5%	
Lead	0.2 (Max)	
Zinc	Rem	

ALLOY DESIGNATIONS		
UNS	C46400	
JIS	C4640	
BS	CZ112(CW712R)	

SHEET/PLATE SPECIFICATIONS	
Thickness (mm)*	0.3- 25.00
Width (mm) *	≤1250
Length(mm)*	≤2500

CHARACTERISTICS

Commercial Name is Naval Brass.

MEI-62 isbrass alloy with Tin content and is highly resistant to corrosion.

	MECHANICAL PROPERTIES			
Temper	Condition	Tensile Strength MPa / Ksi (Min)	Yield Stress MPa/ Ksi (Min)	Elongation % (Min)
Hotrolled & annealed	0	340 /50	140/20	25
As Hot rolled	M	340/50	140/20	25

PHYSICAL PROPERTIES				
TYPICAL VALUES IN ANNEALED TEMPER AT 20 ° C				
Density	Electrical conductivity IACS)	Thermal Conductivity (W/m.K)	Modulus of Elasticity Gpa	Specific Heat J/kg.K (%
8.41	26	116	103	375

MITTAL ENGINEERING INDUSTRIES OLD BILASPUR ROAD , JAGADHRI-135003 (HARYANA) Website-mittalenggind.in



MEI-62(CuZn37 Sn1.5) ROLLED PRODUCTS

Fabrication	Properties
TECHNIQUE	SUITABILITY
Soldering	Excellent
Brazing	Excellent
Oxyacetylene Welding	Good
Gas Shielded Arc Welding	Fair
Coated Metal Arc Welding	Not Recommended
Spot Weld	Good
Seam Weld	Fair
Butt Weld	Good
Capacity for Being cold worked	Fair
Capacity for Being Hot Formed	Excellent
Forgeability Rating	90
Machinability Rating	30

CORROSION RESISTANCE

Wrought strengthening and the addition of tin makes MEI-62 highly resistance to dezincification, greatly inhabiting seawater corrosion at higher-than-normal temperatures.CZ112(CW712R)Naval Brass is resistant to wear, fatigue, galling, and stress corrosion cracking. It also offers good strength levels combined with an excellent hot formability. Its uses are mainly in seawater application such as marine hardware balls, nuts, bolts, rivers, valve, stems and propeller shafts.

Packaging

Standardseaworthypackaging or asperspecific requirements of customer.

TYPICAL APPLICATIONS

Precision Shipboard Equipment,
Pressure Vessels, Condenser Plates, Heat
Exchanger Plates, valve guides, Decorative Fitting,
Turn buckles, Marine Hardware, Missile
components, and Baffle Plates.

MEI-62 conform ROHS Directive

This dataisgeneraltechnical productinformation. Bindingtechnical features are subject to the contract.